

SPEED DRY MIX – VINTAGE STUCCO

Water Resistant Cement Based Polymer Modified leveling Stucco

Available in 40/25 kg bag, in dry form; No curing is required after application

PRODUCT

This product has been introduced by keeping in view of Best Global Construction Practices .

Vintage Stucco, is suitable for all Internal /External walls , Ceilings , soffits etc . Product is designed in such a way that, thickness of 2-6 mm can be achieved easily in single coat. It can be applied in multiple coats . It is a Specially formulated Grey/ White Cement Based Polymer Modified Stucco that does not require any curing post application. High Quality Mineral Fillers (graded) and Polymers are used while manufacturing the product.

FEATURES AND BENEFITS

- High Adhesion - becomes an integral part of the substrate.
- No hacking is required on substrate.
- No curing is required post application.
- Can be applied with Stucco Trowel /Spray Machine
- No shrinkage Cracks
- Consistent Quality
- Excellent Spreadability.
- Durable

PRODUCT DATA

Colour	White
Main Binder	White Cement
Fillers	Graded silt free Sand and Limestone fillers
Polymers	Special Polymers having a) adhesion and b) Self Curing Properties
Bulk Density	1250-1350 Kg/CuM
Coverage	1.40 kg/Sqm/mm on plain surface. Coverage from 40kg bag.
Pot Life	90 mins
Compressive Strength, 28 day	9.50- 12.00 N/mm ²
Tensile Adhesion ,28 day	More than 0.8 N/mm ²
Shelf Life	6 Months

SURFACE PREPARATION

Surface must be free of dust /loose particles, grease, mould oil , rust metal, wood peels , paints and plastics . Surface must be dampened / pre-moistened at least 15 minutes before the application of Vintage Stucco.

MIXING AND APPLICATION

Approx. 25% water (by weight of material) is required for mixing . For better results ,mixing should be preferably done with mechanical mixer/stirrer. Mixing would normally take about 5 minutes . The material should be applied within 90 mins of preparation. It can be applied in multiple layers.

CURING

No curing is required. Natural air curing is enough.

STORAGE AND PACKING

Speed Dry Mix – Vintage Stucco is delivered in 40/25 Kg bag. Storage life is Six months . Material should be stored in a dry place .

HEALTH AND SAFETY

- Recommend to wear NIOSH approved or equivalent particulate face mask while mixing the material.
- Keep out of reach of children.
- Although Product contains only Non-toxic materials , care should be taken to avoid dust inhalation while mixing and handling

DISCLAIMER

It is assumed that all standard Civil Engineering Practices shall be adopted for application of Vintage Stucco . The information given in this leaflet is for general guidance only.